



Ulbrich Stainless Steels & Special Metals, Inc. • 153 Washington Avenue • North Haven, CT 06473 USA • 800-243-1676 • ULBRICH.com

416 STAINLESS STEEL, UNS S41600

Wire, AMS 5610, ASTM A582, QQ-S-764, Mil-W-5263

Applications

Type 416 stainless steel is used for shafts, axles, gears, screws, bolts and any part that requires considerable machining. Should not be used for vessels under high pressures.

Description

Type 416 stainless steel is a martensitic, free machining grade that can be hardened by heat treating to increase strength and hardness. The alloy exhibits machinability that is better than austenitic grades but sacrifices corrosion resistance.

Chemistry Typical

Carbon: 0.15 max

Phosphorus: 0.060 max

Silicon: 1.00 max Manganese: 1.25 max Sulfur: 0.150 min

Chromium: 12.00-14.00

Physical Properties

Density: 0.282 lbs/in3 7.80 g/cm3

Electrical Resistivity: ohm-cir-mil/ft:

At 70 °F (21 °C): 343.0

Specific Heat: BTU/lb-°F (J/g-°C): 32 - 212 °F (0 - 100 °C): 0.110 (0.460)

Thermal Conductivity: BTU-in//hr-ft²-°F (W/m•K)

At 200 °F (94 °C): 172.8 (24.9) At 1000 °F (538 °C): 198 (28.5)

Limitation of Liability and Disclaimer of Warranty: In no event will Ulbrich Stainless Steels & Special Metals, Inc., be liable for any damages arising from the use of the information included in this document or that it is suitable for the 'applications' noted. We believe the information and data provided to be accurate to the best of our knowledge but, all data is considered typical values only. It is intended for reference and general information and not recommended for specification, design or engineering purposes. Ulbrich assumes no implied or express warranty in regard to the creation or accuracy of the data provided in this document. Copyright January 2014 Revision 06.01.2015. Ulbrich Stainless Steels & Special Metals, Inc. All rights reserved.

416 STAINLESS STEEL

Mean Coefficient of Thermal Expansion: µin/in-°F (µm/m-°C)

32 - 212 °F (0 - 100 °C): 5.50 (9.90) 32 - 600 °F (0 - 316 °C): 5.60 (10.1)

32 - 1200 °F (0 - 649 °C): 6.5 (11.7)

Modulus of Elasticity: KSI (MPa) 29.0 x 10³ (200 x 10³) in tension

Melting Range: 2700 - 2790 °F (1488 - 1530 °C)

Forms

Sheet, Strip, Plate – Inquiry with Ulbrich Stainless Steel Sales Wire – Profile, Round, Square Rectangular cross sections – Inquiry with Ulbrich Shaped Wire Sales

Mechanical Properties at Room Temperature

Properties: Annealed

Ultimate Tensile Strength: 75 KSI min (517 MPa min)

Yield Strength: 40 KSI min (276 MPa min)

Elongation: 30 % min

Properties: Tempered

Type 416 can be cold worked to various tempers. Contact Ulbrich Shaped Wire Technical Service for additional information.

Additional Properties

Corrosion Resistance

Refer to NACE (National Association of Corrosion Engineers) for recommendations.

Wire Finishes

XC – Extra clean bright annealed or bright annealed and cold rolled Grease – Ultra-bright finish (for decorative applications)
Soap – Soap is not removed from tempered wire to act as a lubricant.

Heat Treatment

Type 416 can be hardened by cold working and by heat treatment.

Welding

For best results refer to: SSINA's "Welding of Stainless Steels and Other Joining Methods".

Limitation of Liability and Disclaimer of Warranty: In no event will Ulbrich Stainless Steels & Special Metals, Inc., be liable for any damages arising from the use of the information included in this document or that it is suitable for the 'applications' noted. We believe the information and data provided to be accurate to the best of our knowledge but, all data is considered typical values only. It is intended for reference and general information and not recommended for specification, design or engineering purposes. Ulbrich assumes no implied or express warranty in regard to the creation or accuracy of the data provided in this document. Copyright January 2014 Revision 06.01.2015. Ulbrich Stainless Steels & Special Metals, Inc. All rights reserved.

We Deliver Precision

^{*} Contact Ulbrich Wire with special finish requests.