



We Deliver Precision®

ULBRICH.COM

DEVELOPMENT PARTNERSHIP

Braid Wire **Accelerator**® PROGRAM



At Ulbrich, we understand medical device development timelines continue to be reduced. The need for device designers to iterate quickly is accelerating and rarely supported by the supply chain. To better serve our customers' ever increasing requirements, we have developed our fine wire stocking program.

- » We provide you the ability to obtain a variety of round and flat wire quickly
- » This program can have wire in your hands in 72 hours or less
- » Product ships within 24 hours of order acknowledgement
- » Your project teams are now able to meet their timelines while incorporating all the design performance characteristics your devices require
- » Need minor modifications? Ask about our semi-finished-materials program!

ULBRICH SPECIALTY WIRE PRODUCTS
692 Plant Road, Westminster, SC 29693 USA
+1 864 647 6087
info@ulbrich.com

© 2024 Ulbrich Stainless Steels & Special Metals, Inc.

ULBRICH OF AUSTRIA GMBH
Industriestraße 1, 7052 Müllendorf, Austria
+43 2682 61897 0
austria@ulbrich.com

Material	Size in	Tensile Range ksi	Winding Tension	Bobbin Type	Feet/Bobbin	Part Number
304V	.0005" x .0025"	300-355 ksi	50 grams	Steeger 30mm	5,000	7894-7012
304V	.0005" x .003"	300 ksi min	60 grams	Steeger 30mm	5,000	7894-7011
304V	.0007" x .003"	300 ksi min	50 grams	Steeger 30mm	5,000	7894-7014
304V	.001" x .003"	150-180 ksi	50 grams	Steeger 30mm	5,000	7894-7000
304V	.001" x .003"	200-250 ksi	50 grams	Steeger 30mm	5,000	7894-7002
304V	.001" x .003"	300-355 ksi	50 grams	Steeger 30mm	5,000	7894-7001
304V	.001" x .003"	High Tensile 400 ksi min	75 grams	Steeger 30mm	5,000	7894-7024
304V	.001" x .005"	150-200 ksi	75 grams	Steeger 30mm	5,000	7894-7003
304V	.001" x .005"	200-250 ksi	50 grams	Steeger 30mm	5,000	7894-7004
304V	.001" x .005"	300 ksi min	75 grams	Steeger 30mm	5,000	7894-7005
304V	.002" x .005"	300 ksi min	85 grams	Steeger 30mm	2,500	7894-7016
304V	.002" x .006"	300 ksi min	100 grams	Steeger 30mm	2,500	7894-7015
304V	.0015" x .005"	300 ksi min	75 grams	Steeger 30mm	5,000	7894-7023
304V	.0005" x .0015"	300 ksi min	60 grams	Steeger 30mm	5,000	7894-7041
304V	.0015" Rd	300 ksi min	75 grams	Steeger 30mm	5,000	7894-7038
304V	.00075" Rd	300 ksi min	25 grams	Steeger 30mm	5,000	7894-7022
304V	.001" Rd	235-265 ksi	25 grams	Steeger 30mm	5,000	7894-7006
304V	.001" Rd	300 ksi min	40 grams	Steeger 30mm	5,000	7894-7007
304V	.001" Rd	High Tensile 425 ksi min	25 grams	Steeger 30mm	5,000	7894-7026
304V	.0015" Rd	235-265 ksi	50 grams	Steeger 30mm	5,000	7894-7013
304V	.002" Rd	151-200 ksi	50 grams	Steeger 30mm	5,000	7894-7008
304V	.002" Rd	235-265 ksi	50 grams	Steeger 30mm	5,000	7894-7009
304V	.0005" Rd	300 ksi min	15 grams	Steeger 30mm	5,000	7894-7025
304V	.002" Rd	300 ksi min	50 grams	Steeger 30mm	5,000	7894-7010
304V	.002" Rd	High Tensile 425 ksi min	75 grams	Steeger 30mm	5,000	7894-7027
304V	.002" Dual-lead	300 ksi min	50 grams	Steeger 30mm	5,000	7894-7021
304V	.002" 3 ends	300 ksi min	50 grams	Steeger 30mm	4,200	7894-7028
304V	.002" 4 ends	300 ksi min	50 grams	Steeger 30mm	4,000	7894-7029
304V	.003" Rd	300 ksi min	100 grams	Steeger 30mm	4,000	7894-7017
Nitinol	.001" Rd	As Drawn, Oxide Finish	30 grams	DIN 100	2,500	7990-7100
Nitinol	.001" Rd	As Drawn, Oxide Finish	35 grams	Steeger 30mm	1,000	7990-7101
Nitinol	.002" Rd	As Drawn, Oxide Finish	60 grams	DIN 100	2,500	7990-7102
Nitinol	.002" Rd	As Drawn, Oxide Finish	60 grams	Steeger 30mm	1,000	7990-7103
Nitinol	.003" Rd	As Drawn, Oxide Finish	60 grams	DIN 100	2,500	7990-7104
Nitinol	.003" Rd	As Drawn, Oxide Finish	85 grams	Steeger 30mm	1,000	7990-7105
Tungsten	.001" x .003"	400 ksi min	75 grams	Steeger 30mm	500	7894-7042
Tungsten	.0005" x .0015"	400 ksi min	75 grams	Steeger 30mm	500	7894-7043
Tungsten	.0005" x .003"	400 ksi min	75 grams	Steeger 30mm	500	7894-7044
Tungsten	.0005" Rd	450 ksi min	40 grams	Steeger 30mm	1,000	7894-7039
Tungsten	.0007" Rd	450 ksi min	75 grams	Steeger 30mm	1,000	7894-7040
Tungsten	.001" Rd	400 ksi min	75 grams	Steeger 30mm	2,500	7894-7030
Tungsten	.002" Rd	400 ksi min	75 grams	Steeger 30mm	2,500	7894-7031
L605	.002" Rd	300 ksi min	75 grams	Steeger 30mm	2,500	7894-7032
L605	.001" x .003"	300 ksi min	75 grams	Steeger 30mm	2,500	7894-7033
CuBe 172	.002" Rd	185-245 ksi	75 grams	Steeger 30mm	2,500	7894-7034
CuBe 172	.001" x .003"	185-245 ksi	75 grams	Steeger 30mm	2,500	7894-7035
MP35N	.002" Rd	300 ksi min	75 grams	Steeger 30mm	2,500	7894-7036
MP35N	.001" x .003"	300 ksi min	75 grams	Steeger 30mm	2,500	7894-7037

All information provided is based on our current standard knowledge and does not claim to be exhaustive.
This information may not be passed on to third parties without approval by Ulbrich Specialty Wire Products.
All rights reserved. © 2024 Ulbrich Stainless Steels & Special Metals, Inc.

Material	Size mm	Tensile Range MPa	Winding Tension g	Bobbin Type	m/Bobbin	Part Number
304V	0.013 x 0.064	2068 – 2448	50	Steeger 30mm	1525	7894-7012
304V	0.013 x 0.076	2068 min	60	Steeger 30mm	1525	7894-7011
304V	0.018 x 0.076	2068 min	50	Steeger 30mm	1525	7894-7014
304V	0.025 x 0.076	1034 – 1241	50	Steeger 30mm	1525	7894-7000
304V	0.025 x 0.076	1379 – 1724	50	Steeger 30mm	1525	7894-7002
304V	0.025 x 0.076	2068 – 2448	50	Steeger 30mm	1525	7894-7001
304V	0.025 x 0.076	High Tensile 2758 min	75	Steeger 30mm	1525	7894-7024
304V	0.025 x 0.127	1034 – 1379	75	Steeger 30mm	1525	7894-7003
304V	0.025 x 0.127	1379 – 1724	50	Steeger 30mm	1525	7894-7004
304V	0.025 x 0.127	2068 min	75	Steeger 30mm	1525	7894-7005
304V	0.051 x 0.127	2068 min	85	Steeger 30mm	760	7894-7016
304V	0.051 x 0.152	2068 min	100	Steeger 30mm	760	7894-7015
304V	0.038 x 0.127	2068 min	75	Steeger 30mm	1525	7894-7023
304V	0.013 x 0.038	2068 min	60	Steeger 30mm	1525	7894-7041
304V	0.038 Rd	2068 min	75	Steeger 30mm	1525	7894-7038
304V	0.019 Rd	2068 min	25	Steeger 30mm	1525	7894-7022
304V	0.025 Rd	1620 – 1827	25	Steeger 30mm	1525	7894-7006
304V	0.025 Rd	2068 min	40	Steeger 30mm	1525	7894-7007
304V	0.025 Rd	High Tensile 2930 min	25	Steeger 30mm	1525	7894-7026
304V	0.038 Rd	1620 – 1827	50	Steeger 30mm	1525	7894-7013
304V	0.051 Rd	1041 – 1379	50	Steeger 30mm	1525	7894-7008
304V	0.051 Rd	1620 – 1827	50	Steeger 30mm	1525	7894-7009
304V	0.013 Rd	2068 min	15	Steeger 30mm	1525	7894-7025
304V	0.051 Rd	2068 min	50	Steeger 30mm	1525	7894-7010
304V	0.051 Rd	High Tensile 2930 min	75	Steeger 30mm	1525	7894-7027
304V	0.051 Dual-lead	2068 min	50	Steeger 30mm	1525	7894-7021
304V	0.051 3 ends	2068 min	50	Steeger 30mm	1280	7894-7028
304V	0.051 4 ends	2068 min	50	Steeger 30mm	1220	7894-7029
304V	0.076 Rd	2068 min	100	Steeger 30mm	1220	7894-7017
Nitinol	0.025 Rd	As Drawn, Oxide Finish	30	DIN 100	760	7990-7100
Nitinol	0.025 Rd	As Drawn, Oxide Finish	35	Steeger 30mm	305	7990-7101
Nitinol	0.051 Rd	As Drawn, Oxide Finish	60	DIN 100	760	7990-7102
Nitinol	0.051 Rd	As Drawn, Oxide Finish	60	Steeger 30mm	305	7990-7103
Nitinol	0.076 Rd	As Drawn, Oxide Finish	60	DIN 100	760	7990-7104
Nitinol	0.076 Rd	As Drawn, Oxide Finish	85	Steeger 30mm	305	7990-7105
Tungsten	0.025 x 0.076	2758 min	75	Steeger 30mm	152	7894-7042
Tungsten	0.013 x 0.038	2758 min	75	Steeger 30mm	152	7894-7043
Tungsten	0.013 x 0.076	2758 min	75	Steeger 30mm	152	7894-7044
Tungsten	0.013 Rd	3103 min	40	Steeger 30mm	305	7894-7039
Tungsten	0.018 Rd	3103 min	75	Steeger 30mm	305	7894-7040
Tungsten	0.025 Rd	2758 min	75	Steeger 30mm	760	7894-7030
Tungsten	0.051 Rd	2758 min	75	Steeger 30mm	760	7894-7031
L605	0.051 Rd	2068 min	75	Steeger 30mm	760	7894-7032
L605	0.025 x 0.076	2068 min	75	Steeger 30mm	760	7894-7033
CuBe 172	0.051 Rd	1275 – 1689	75	Steeger 30mm	760	7894-7034
CuBe 172	0.025 x 0.076	1275 – 1689	75	Steeger 30mm	760	7894-7035
MP35N	0.051 Rd	2068 min	75	Steeger 30mm	760	7894-7036
MP35N	0.025 x 0.076	2068 min	75	Steeger 30mm	760	7894-7037

All information provided is based on our current standard knowledge and does not claim to be exhaustive.
This information may not be passed on to third parties without approval by Ulbrich Specialty Wire Products.
All rights reserved. © 2024 Ulbrich Stainless Steels & Special Metals, Inc.